


			Ambiance
<b>DESCRIPTION</b>			
Total thickness	EN 428	mm	2
Weight	EN 430	g/m <sup>2</sup>	3420
Width of sheet	EN 426	cm	200
Length of sheet	EN 426	lm	20
<b>CLASSIFICATION</b>			
Norm / Product specification			EN 649
European classification	EN 685	class	34 - 43
K rating	-	class	K5
Fire rating	EN 13 501-1	class	B <sub>fl</sub> -s1
Marine Equipment Directive	Directive 96/98/EC		
International Maritime Organisation	I.M.O code F.T.P.	n°	WARRINGTON MED0180TE
Static electrical propensity	EN 1815	kV	< 2
Electrical resistance	EN 1081	Ohm	≥ 1 x 10 <sup>9</sup>
Slip resistance wet: ramp test with oil	DIN 51130	class	R9
<b>PERFORMANCE</b>			
Wear resistance	EN 660.1	mm	≤ 0.20
Wear Group	EN 649	group	M
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation	EN 433	mm	~ 0.03
Thermal conductivity	EN 12 524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	class	OK
Anti-bacterial and fungicidal treatment	-	-	OK
Surface treatment	-	-	PUR
<b>CE MARKING</b>			
	EN 14041		