


<b>Tarasafe Uni</b>			
<b>DESCRIPTION</b>			
Total thickness	EN 428	mm	2.00
Thickness of wearlayer	EN 429	mm	≥0.9
Weight	EN 430	g/m <sup>2</sup>	2 645
Width of sheet	EN 426	cm	200
Length of sheet	EN 426	lm	20
<b>CLASSIFICATION</b>			
Norm			EN 649
European classification	EN 685	class	34 - 43
K rating		class	K5
Fire rating	EN 13501-1	class	B <sub>f1</sub> -s1
Static electrical propensity	EN 1815	kV	< 2
RRL pendulum test (wet test)	BS 7976	°	≥ 36
Surface roughness R <sub>tm</sub>		µm	≥ 20
Slip resistance wet	DIN 51 130	class	R10
<b>PERFORMANCE</b>			
Wear resistance	EN 660.1	mm	≤0.08
Wear group			T
Dimensional stability	EN 434	%	≤0.40
Residual indentation	EN 433	mm	≤0.10
Impact sound insulation	EN ISO 717-2	dB	
Thermal conductivity	EN 12 524	W/(m.K)	» 0.25
Colour fastness	EN 20 105 B02	degree	≥6
Chemical products resistance	EN 423		good
Anti-bacterial and fungicidal treatment			Sanosol®
Surface treatment			Sparclean®
<b>CE MARKING</b>			
	EN 14041		