


Nera Classic				
DESCRIPTION				
Total thickness	EN 428	mm	2.25	2.2
Thickness of wearlayer	EN 429	mm	≥ 0.60	0.55
Weight	EN 430	g/m ²	2815	2425
Width of sheet	EN 426	cm	200	400
Length of sheet	EN 426	lm	20	20
CLASSIFICATION				
Norm / Product specification			EN 649	EN 653
European classification	EN 685	class	33 - 42	33 - 42
Fire rating	EN 13 501-1	class	B _{fl} -s1	B _{fl} -s1
Static electrical propensity	EN 1815	kV	< 2	< 2
PERFORMANCE				
Wear resistance	EN 660.1	mm	≤ 0.08	≤ 0.08
Wear group	EN 649	-	T	T
Dimensional stability	EN 434	%	≤ 0.40	≤ 0.40
Residual indentation	EN 433	mm	≤ 0.05	≤ 0.10
Impact sound insulation	EN ISO 717-2	dB	5	8
Thermal conductivity	EN 12 524	W/(m.K)	0.25	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6	≥ 6
Chemical products resistance	EN 423	-	OK	OK
Anti-bacterial and fungicidal treatment	-	-	Sanosol®	Sanosol®
Surface treatment	-	-	PUR	PUR
CE MARKING				
	EN 14041		