




DESCRIPTION			COMPACT
Total thickness	EN ISO 24346 (EN 428)	mm	2.00
Thickness of wearlayer	EN ISO 24340 (EN 429)	mm	0.70
Weight	EN ISO 23997 (EN 430)	g/m ²	2635
Width of sheet	EN ISO 24341 (EN 426)	cm	200
Length of sheet	EN ISO 24341 (EN 426)	lm	25
CLASSIFICATION			
Norm / Product specification	-	-	EN ISO 10582 (EN 649)
European classification	EN 685	class	34 - 43
Fire rating	EN 13501-1	class	B _{fl} -s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance : Pendulum Test (1)	BS 7976-2	PTV	> 36
Surface roughness R _{tm}	-	µm	R _z ≥ 20
Slip resistance wet: ramp test	DIN 51130	class	R11
PERFORMANCES			
Wear resistance	EN 660.2	mm ³	≤ 2.0
Wear group	NF 189	group	T
Type Binder content	EN ISO 10582	type	I
Dimensional stability	EN ISO 23999 (EN 434)	%	≤ 0.40
Residual indentation (requirement)	EN ISO 24343-1 (EN 433)	mm	≤ 0.10
Residual indentation (measure)	-	mm	≈ 0.03
Impact sound insulation	EN ISO 717-2	dB	8
Castor chair test (type W)	EN ISO 4918 (EN 425)	-	OK
Thermal conductivity	EN ISO 10456 (EN 12524)	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Surface treatment	-	-	Protecsol® Control
Chemical products resistance	EN ISO 26987 (EN 423)	-	OK
Anti-bacterial activity (E. coli – S. aureus -MRSA) (2)	ISO 22196	-	> 99% Inhibits growth
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 70
Certification	-	-	Floorscore®
CE MARKING			
	EN 14041		
			

(1) The RRL pendulum test : wet is expressed as a pendulum test Value (PTV) and a Slip Resistance Value (SRV) to show that the test was carried out using a 4S rubber resistor pad in accordance HSE guidance (for longer lifetime sustainable wet resistance, please refer to Tarasafe ranges)

(2) The implementation of an effective cleaning regime is the best defence against infection