

DESCRIPTION

Total thickness	EN 428	mm	3.20
	ASTM F386-02	inch	0.126
Wearlayer thickness	EN 429	mm	1.16
	ASTM F410-02	inch	0.046
Weight	EN 430	g/sq.m	3080
Width of sheet	EN 426	cm	200
	-	feet - inch	6'6"
Length of sheet	EN 426	lm	20
	-	feet - inch	66'
Coverage / roll	-	sq.ft	0
	-	sq.m	40



CLASSIFICATION

Norm / Product specification	-	-	EN 651
	ASTM F1303-04	-	
European classification	EN 685	class	34 - 43
Fire rating	EN 13501-1	class	B _{fl} -s1
	ASTM E648-08	class	class I
	CAN/ULC S102.2	-	-
Static electrical propensity	EN 1815	kV	< 2
Slip dry resistance : Pendulum Tester	BS 7976	PTV	
Surface roughness R _{tm}	-	µm	Rz ≥ 20
Slip resistance wet: ramp test with oil	DIN 51 130	class	R11

PERFORMANCE

Wear resistance	EN 660.1	mm ³	≤ 2
Wear group	EN 651	group	
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation	EN 433	mm	≤ 0.20
Impact sound insulation	EN ISO 717-2	dB	16
Thermal conductivity	EN 12524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Anti-bacterial and fungicidal treatment	-	-	Sanosol®
Surface treatment	-	-	SparClean®
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 100

CE MARKING

	EN 14041	-	
		-	