

## EUROPEAN REACTION TO FIRE CLASSIFICATION REPORT ACCORDING TO THE EUROPEAN STANDARD EN 13501-1

Notified Body by the French State besides the European Commission under number : 0071

Product standard : NF EN 14041  
Resilient, textile and laminate floorcoverings

(free translation of French classification report n° F070207 CEMATE/3)

**N°F070207 - CEMATE/4**

**Material submitted by :** GERFLOR SA  
50 Cours de la République  
69627 VILLEURBANNE Cedex

**Commercial trademark :** TARALAY/TARADAL CONFORT MATIERES (INDIANA,BRAZILIA,VENEZIA)  
and MASSIF (FORUM,JAMAICA,METALLICA) 33 et 43

**Production site :** GERFLOR Tarare  
43 Boulevard Garibaldi  
69170 TARARE  
FRANCE

**Brief description :** Floorcovering in PVC

**Date of report :** 2005, August 19<sup>th</sup>

**Only full reproduction of the present document is authorized.  
It contains 4 pages**

## 1. INTRODUCTION

This classification report defines the classification assigned to product in accordance with the procedures given in EN 13501-1.

## 2. DETAILS OF CLASSIFIED PRODUCT

### 2.1. NATURE AND END USE APPLICATION

VSM type (NF EN 651 standard) floorcovering

### 2.2. DESCRIPTION

Characteristics of the products :

Products	Thicknesses (mm) Tolerance : -0.15/+0.18 mm	Mass per unit square meter in g/m <sup>2</sup> Tolerance : -10/+13 %
<b>TARALAY/TARADAL CONFORT MATIERES</b>		
INDIANA	3.00	2800
BRAZILIA	3.00	2800
VENEZIA	3.00	2840
<b>TARALAY/TARADAL CONFORT MASSIFS</b>		
FORUM	3.25	3100
JAMAICA	3.25	3100
METALLICA	3.30	3150

Products	Wearing layer Press plasticized PVC	Intercalary Calendered PVC with glass grid reinforced	Backing THD PVC foam
	Thicknesses in mm	Thicknesses in mm	Thicknesses in mm
<b>TARALAY/TARADAL CONFORT MATIERES</b>			
INDIANA	0.95	0.65	1.40
BRAZILIA	1.00	0.60	1.40
VENEZIA	1.00	0.60	1.40
<b>TARALAY/TARADAL CONFORT MASSIFS</b>			
FORUM	1.10	0.75	1.40
JAMAICA	1.25	0.60	1.40
METALLICA	1.10	0.75	1.40

Text report to be followed on next page

### 3. TEST REPORTS AND TEST RESULTS IN SUPPORT OF THIS CLASSIFICATION

#### 3.1. TEST REPORTS

Name of laboratory	Name of sponsor	Test report ref. n°	Test method
Laboratoire national de métrologie et d'essais 29 av. Roger Hennequin 78197 TRAPPES CEDEX	GERFLOR SA 50 Cours de la République 69627 VILLEURBANNE Cedex	File : F070207 CEMATE/1 Date of tests : 2005/06/21	Radiant panel EN ISO 9239-1
		File : F070207 CEMATE/2 Date of tests : 2005/06/16	Radiant panel EN ISO 9239-1

#### 3.2. TEST RESULTS FOR FLOORINGS

Test method	Number of tests	Parameters	Results
EN ISO 9239-1	2		
Glued to a particle board non-FR	<b>TCMI AURORA</b> (4 specimens)	Critical flux (kW/m <sup>2</sup> ) Smoke (%.min)	<b>7.51</b> <b>256</b>
	<b>TL CF Massifs 43 METALLICA</b> (4 specimens)	Critical flux (kW/m <sup>2</sup> ) Smoke (%.min)	<b>6.61</b> <b>402</b>

Text report to be followed on next page