

DESCRIPTION

Total thickness	EN 428	mm	2.00
Thickness of wearlayer	EN 429	mm	1.16
Weight	EN 430	g/m ²	2610
Width of sheet	EN 426	cm	200
Length of sheet	EN 426	lm	20



CLASSIFICATION

Norm / Product specification	-	-	EN 649
European classification	EN 685	class	34 - 43
Fire rating	EN 13501-1	class	B _{f1} -s1
Static electrical propensity	EN 1815	kV	2
Slip resistance : Pendulum Test (dry & wet)	BS 7976-2	PTV	60
Surface roughness R _{tm}	-	µm	10 ≤ Rz < 20
Slip resistance wet: ramp test with oil	DIN 51 130	class	R10
Slip resistance – ramp test	EN 13845 (annex C)	class	ESb

PERFORMANCES

Wear resistance	EN 660.2	mm ³	≤ 2
Wear group	EN 649	group	T
Type Binder content	ISO 10582	type	
Dimensional stability	EN 434	%	≤ 0.40
Impact sound insulation	EN ISO 717-2	dB	
Residual indentation	EN 433	mm	≤ 0.10
Castor chair test (type W)	EN 425	-	P3
Thermal conductivity	EN 12524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥6
Chemical products resistance	EN 423	-	OK
Treatment	-	-	Sanosol®
Surface treatment	-	-	SparClean®
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 100

CE MARKING

	EN 14041	-	
		-	