DLW LINOLEUM
COLORETTE ACOUSTICPLUS 19dB

DESCRIPTION			
Total thickness	EN ISO 24346	mm	4.0
Backing	-	-	Foam
Thickness of foam backing	EN ISO 24340	mm	1.5
Weight	EN ISO 23997	g/sqm	3500
Width of sheet	EN ISO 24341	cm	200*
Length of sheet	EN ISO 24341	m	20 - 31*
Material content	98% natural materials (bio-based and mineral) : linseed oil, wood flour, resins, cork, minerals, jute fabric, among which 76% are rapidly renewable. 100 % recyclable, contains up to 40 % recycled material.		
CLASSIFICATION			
Norm / Product specification	-	-	EN 686
European classification	EN ISO 10874	class	23 / 33 / 41
Fire rating	EN 13501-1	class	Cfl-s1**
Slip resistance	DIN 51130 – BGR 181	class	R9
Impact sound insulation	EN ISO 717-2	dB	19 dB
PERFORMANCES			
Residual indentation	EN ISO 24343-1	mm	≤ 0.30
Colour fastness	EN ISO 105 - B02	degree	≥6
Point contact resistance	VDE 0100	kOhm	>200
Static electrical propensity	EN 1815	kV	< 2.0
Castor chair test (Type W)	ISO 4918	-	OK
Thermal resistance	EN 12667	Sqm,K/W	0.044
Thermal conductivity	EN ISO 10456	W/(m.K)	0.0937
Surface treatment	-	-	Neocare
Chemical products resistance	EN ISO 26987	class	OK
Anti-bacterial activity (E. coli – S. aureus – MRSA)***	EN ISO 22196 (JIS Z 2801)	-	> 99,99% inhibits growth after 24h
Anti-viral activity (Human coronavirus)**	ISO 21702	-	> 98,65 % virucidal activity after 5h
INDOOR AIR QUALITY			
TVOC after 28 days	EN 16516	µg/m³ (Micrograms)	< 10
CIRCULAR ECONOMY			
Certification	Cradle to Cradle	-	Bronze
CERTIFICATES AND LABELS			
CE MARKING			
CE	EN 14041 : 2004 AC : 2006	-	DS, Cfl-s1

* Roll dimension:1,96m x 18-29lm for SRP product codes R899/R904/R906/R908/R909/R910/R921
** Glued according to certificate.
*** The implementation of an effective cleaning method is the best defense against infection

DOP numbers available from your local branch.

Depending on light exposure, the product color can vary, due to linoleum natural oxidization process. The process is reversible.

We recommend that the samples be exposed to sunlight for several hours prior to making a final color choice